

Contact VA 2500 HT Cyanoacrylate Adhesive

Contact Cyanoacrylate Adhesives



Cyanoacrylate adhesive for special requirements | high-temperature-resistant | high viscosity | slow curing | cures with residual elasticity | high peel and impact strength

Due to its curing with residual elasticity, WEICON Contact VA 2500 HT is particularly suitable under changing climatic conditions. It is insensitive even under a longer influence of humidity. Contact VA 2500 HT is suited for the bonding of the most diverse rubber materials and plastics and also for metal/plastic joints. VA 2500 HT can be used in many different industrial areas.

Technische Daten

Base		ethyl
Colour		beige, opaque
Texture		opaque
Gap bridging up to max.		0,2 mm
Initial adhesion on aluminium		40 - 80 sec.
Initial adhesion on NBR rubber		25 - 60 sec.
Initial adhesion on rigid PVC		25 - 100 sec.
Final strength (100 % strength)		24 h
Steel sandblasted	DIN EN 1465	24 N/mm ²
Aluminium sandblasted	DIN EN 1465	18 N/mm ²
Rigid PVC	DIN EN 1465	13 N/mm ²
ABS	DIN EN 1465	12 N/mm ²
NBR	DIN EN 1465	> 8 N/mm ²
Temperature resistance		-55°C to +140°C /softening temp. +160°C
ISSA Code		75.629.10/11/18/19
IMPA Code		815249/50/51/52

FENG FU PRIVATE LTD
www.fengfupte.com
Email: fengfu@ffpte.com
Whatsapp: +65 8854 6437
Call us at: +65 9816 1980

Surface pre-treatment

For a flawless adhesive bond, surfaces must be clean and dry (clean and degrease with WEICON Surface Cleaner). Smooth surfaces should be roughened mechanically. To improve the adhesion of plastics difficult to bond (e.g. PE, PP, POM, PTFE), thermoplastic elastomers (TPE) and silicones, WEICON CA-Primer can be applied to the bonding surface.

Processing

- Apply WEICON Contact Cyanoacrylate Adhesive to just one of the bonding surfaces.
- The layer thickness when applying the adhesive should be between min. 0.05 and max. 0.2 mm (depending on the type), as otherwise complete curing cannot be guaranteed.
- For large-surface bondings, WEICON Contact Cyanoacrylate Adhesives should be applied in dots in order to prevent inner tensions.
- WEICON Contact Cyanoacrylate Adhesives are very economical. One drop covers approx. 3 to 5 cm² bonding surface.
- The components should be bonded at a relative air humidity level between 40% and 80%. Below 40 %, the curing process is slowed down significantly or even prevented altogether. At an air humidity level above 80 % or with strongly basic substrates (e.g. glasses), the risk of shock-curing occurs. In these cases, certain materials show a drop in strength by 10 % to 15 % due to tensions in the adhesive layer.

- Alkaline surfaces (pH value >7) accelerate the curing process, acidic surfaces (pH value <7) slow down the curing process and can prevent polymerisation altogether in extreme cases.

Storage

WEICON Contact Cyanoacrylate Adhesives have a shelf life of at least 9 months, when stored in unopened condition at room temperature (+18 °C to +25 °C) in a dry and dark space. Temperatures of approx. +5 °C will increase the shelf life to 12 months.

Safety and health

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our safety data sheets (www.weicon.com) must be observed.

Accessories

12955170 Dosing Tip, 1 PCE
12955175 Dosing Tip, 1 PCE

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

Contact VA 2500 HT Cyanoacrylate Adhesive

1-Component Adhesives and Sealants Contact Cyanoacrylate Adhesives

Available sizes:

- 12550012 Contact VA 2500 HT Cyanoacrylate Adhesive, 12 g, beige, opaque
- 12550030 Contact VA 2500 HT Cyanoacrylate Adhesive, 30 g, beige, opaque
- 12550060 Contact VA 2500 HT Cyanoacrylate Adhesive, 60 g, beige, opaque
- 12550500 Contact VA 2500 HT Cyanoacrylate Adhesive, 0,5 kg, beige, opaque

Conversion table

$(^{\circ}\text{C} \times 1,8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8,851 = \text{lb}\cdot\text{in}$
$\text{mm}/25,4 = \text{inch}$	$\text{Nm} \times 0,738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25,4 = \text{mil}$	$\text{Nm} \times 141,62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0,225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0,571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25,4 = \text{V}/\text{mil}$

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON GmbH & Co. KG (Headquarters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti. Turkey phone +90 (0) 212 465 33 65 info@weicon.com.tr

To the product detail page:

FENG FU PRIVATE LTD
www.fengfupte.com
Email: fengfu@ffpte.com
Whatsapp: +65 8854 6437
Call us at: +65 9816 1980

