

VA 30 Black Cyanoacrylate Adhesive

Contact Cyanoacrylate Adhesives



Cyanoacrylate adhesive for special requirements | rubber-filled | high-temperature-resistant | medium viscosity | longer curing | cures with residual elasticity | high peel and impact strength

Because of its curing with residual elasticity, WEICON Contact VA 30 Black is particularly suitable for use in changing climate conditions. It is insensitive even to prolonged exposure to humidity. VA 30 Black is suitable for the bonding of diverse rubber materials such as solid rubber or cellular rubber, plastics and metal/plastic joints. WEICON Contact VA 30 Black can be used in various fields of industry.

Characteristics

Base	ethyl
Texture	liquid
Colour after curing	black
Silicone-free	yes

Processing

Processing temperature	+15 °C to +40 °C
Relative air humidity	40% - 70%
Viscosity	250 - 300
Density (+20 °C)	1,1 g/cm ³
Gap bridging up to max.	0,2 mm

Curing

Initial adhesion in seconds (shear strength: 0,5 MPa)	
- measured at	23 °C and 50 % relative humidity
on aluminium sandblasted	20-30 sec.
on ABS untreated	40-50 sec.
on rigid PVC	5-6 min.
Final strength (100 % strength)	24 h

Mechanical properties after curing

Shear strength according to DIN EN 1465	
Steel sandblasted	11-22 MPa
Aluminium sandblasted	7-18 MPa
Rigid untreated PVC	7-14 MPa
Untreated ABS	6-11 MPa
PC (polycarbonate)	7-13 MPa

Thermal parameters


Temperature resistance	-55°C to +140°C
Softening temperature	+150 °C
Thermal expansion coefficient	~ 80 x 10 ⁻⁶ m/(m·K)
Thermal conductivity	DIN EN ISO 22007-4 ~0,1 W/m·K

Electrical parameters

Resistance	DIN IEC93	>10 ¹⁵ Ω·cm
Dielectric strength		~ 25 kV/mm

Approvals / Guidelines

ISSA Code	75.629.60/61/62/63
IMPA Code	815253/54/55/56
MIL-Spec	comply with MIL-A-46050C Type II Class 2



Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface pre-treatment

The successful application of WEICON Contact Cyanoacrylate Adhesives depends on the thorough preparation of the surfaces. This is the most important factor for overall success. Dust, dirt and moisture or wetness have a negative impact on the adhesion.

Therefore, before processing WEICON Contact Cyanoacrylate Adhesives, the following points must be observed: For a flawless adhesive bond, adhesive surfaces must be clean and dry (clean and degrease with WEICON Surface Cleaner). Smooth surfaces should be roughened mechanically. To improve the adhesion of plastics that are difficult to bond (e.g. PE, PP, POM, PTFE), thermoplastic elastomers (TPE) and silicones, WEICON CA-Primer can be applied to the bonding surface.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

VA 30 Black Cyanoacrylate Adhesive

1-Component Adhesives and Sealants

Contact Cyanoacrylate Adhesives

Contact Primer for Polyolefines

Without pre-treatment, many plastics cannot or can only be bonded under certain conditions. When these plastics are pre-treated with WEICON Contact Primer, their surface structure changes. This makes it possible to bond plastics that are otherwise difficult to bond, e.g. polyethylene (PE) and polypropylene (PP) from the polyolefine group. Even modern thermoplastic elastomers (TPE), PTFE and related plastics as well as silicones can be bonded, when pre-treated with WEICON Contact Primer.

Processing

The products are supplied ready for use. Depending on the form of delivery, they can be processed by hand directly from the container or with appropriate dosing equipment. Apply WEICON Contact Cyanoacrylate Adhesive to just one of the bonding surfaces. The layer thickness when applying the adhesive should be between min. 0.05 mm and max. 0.2 mm, as otherwise complete curing cannot be guaranteed. For large-surface bondings, WEICON Contact Cyanoacrylate Adhesives should be applied in dots in order to prevent inner tensions. WEICON Contact Cyanoacrylate Adhesives are very economical. One drop is sufficient for an adhesive area of 3 to 5 cm².

Curing

After applying the product, the parts to be bonded must be joined quickly and fixed if possible, since the curing of the products has already started as a result of the humidity in the ambient air or condensed on the bonding surfaces. The components should be bonded at a relative air humidity level between 40 % and 70 %. Below 40 %, the curing process is slowed down significantly or even prevented altogether. At an air humidity level above 70 % or with strongly alkaline substrates (e.g. glasses), there is a risk of shock curing. In these cases, certain materials show a drop in strength by 10 % to 15 % due to tensions in the adhesive layer. Alkaline surfaces (pH value >7) accelerate the curing process, acidic surfaces (pH value <7) slow down the curing process and can prevent polymerisation altogether in extreme cases. If curing is delayed or disturbed by factors such as a too wide adhesive gap, porous or acidic surface, the use of WEICON Contact Activator is recommended.

WEICON Contact Activator

The activator speeds up the curing process of WEICON Contact Cyanoacrylate Adhesives. When applied to absorbing surfaces, e.g. wood or foam etc., and all chemically-treated surfaces, e.g. zinc galvanized metals etc., the activator's effectiveness lasts approx. one minute. On non-absorbent surfaces, the activator's effectiveness lasts up to approx. 12 hours. Use is recommendable with:

- highly viscous WEICON Contact types

- large thickness of the adhesive layer
- absorbing and porous surfaces
- passive materials (alkaline surfaces, like for example zinc-coated metal parts)
- disadvantageous environmental conditions (low temperatures, low air humidity < 30 %).

Storage

WEICON Contact Cyanoacrylate Adhesives have a shelf life of at least 9 months, when stored in unopened condition at room temperature (+18 °C to +25 °C) in a dry and dark space. Temperatures of approx. +5 °C will increase the shelf life to 12 months.

Scope of delivery

Adhesive

Accessories

10024317	Surface Cleaner, 150 ml, transparent
10024313	Surface Cleaner, 400 ml, transparent
10000282	CA-Activator Spray, 150 ml
10033805	CA-Activator Spray AC, 150 ml
10000275	CA Primer for Polyolefines, 10 ml
10000278	CA Primer for Polyolefines, 100 ml
10068262	Dosing Tip, 1 PCE
10068261	Dosing Tip, 1 PCE
10012382	Contact Filler, 30 g, transparent
10063106	Contact Filler, 30 g, black
10059034	CA-Remover, 12 ml
10051358	CA-Remover, 30 ml
10010887	Processing Spatula, 1 PCE

Available sizes

10025827	VA 30 Black Cyanoacrylate Adhesive, 12 g
10025824	VA 30 Black Cyanoacrylate Adhesive, 30 g
10025829	VA 30 Black Cyanoacrylate Adhesive, 60 g
10025987	VA 30 Black Cyanoacrylate Adhesive, 0,5 kg

Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb-in
mm/25.4 = inch	Nm x 0.738 = lb-ft
µm/25.4 = mil	Nm x 141.62 = oz-in
N x 0.225 = lb	mPa·s = cP
N/mm ² x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

FENG FU PRIVATE LTD
www.fengfupte.com
Email: fengfu@ffpte.com
Whatsapp: +65 8854 6437
Call us at: +65 9816 1980

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr

VA 30 Black Cyanoacrylate Adhesive

1-Component Adhesives and Sealants

Contact Cyanoacrylate Adhesives

To the product detail page:



FENG FU PRIVATE LTD
www.fengfupte.com
Email: fengfu@ffpte.com
Whatsapp: +65 8854 6437
Call us at: +65 9816 1980

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquaters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr